

1. Product Profile

StenAst® 2EP MB is a two component, solvent free moisture barrier, epoxy primer for all **Stenkim®** brand polymer-based surface coatings, top coats and joint sealants. Thanks to its specially designed formula it has excellent adhesion to damp concrete. Prevents moisture vapor to pass. It protects the surface and prevents dusting of concrete surfaces.

StenAst® 2EP MB is available in 15 kg sets.

2. Uses

StenAst® 2EP MB is designed mainly to create a moisture barrier between the surface and the coating. It can be applied on 3-day concretes. With its excellent adhesion it will create a perfect primer layer for application of top coats, mortars and sealants such as **StenFloor®**, **StenCoat®**, **StenSeal®**, **StenSport®**, **StenCare®**, especially on concrete surfaces.

It enhances adhesion of polymer modified cement-based materials on old concrete applied for repair or coating purposes. It is also used in filling in the microcracks formed on concrete surface and as surface hardener and dust inhibitor for concrete pavements.

3. Surface Preparation

Surface must be free from loose materials, oil, grease, paint. Contaminants stuck on the surface must be removed. Contaminants penetrated into the concrete must be wiped with chemicals that can dissolve contaminant and must be cleaned with detergent and water. In cases where there is suspicion that the contamination is not removed, it is recommended to conduct an adhesion test before coating.

4. Application

It is helpful to keep the materials at 20-30°C for one day before the application date. During the application, surface and ambient temperature must be minimum 15°C and the temperature must not drop below 15°C for the 24 hours following the application.

StenAst® 2EP MB is prepared for the application by mixing two components. The components are packaged as they will mix at right proportions when one container from each is mixed. First component A is homogenized

Moisture Barrier Epoxy Primer and Surface Protector

Highlights

- Forms a moisture barrier
- Can be applied on damp, green concrete
- Strong primer
- Solvent free
- Provides excellent adhesion for further coating applications
- Fills the microcracks concrete surface
- Forms an impermeable layer
- Inhibits dusting of concrete pavements

for 2-3 minutes. Component B is poured into the vortex that forms in the container of component A and they are mixed for 2-3 minutes more in low speed. Low speed drill is used for mixing.

Manual mixing of the components is not sufficient. The material may not (partially) cure due to insufficient mixing. There must not be unmixed material left on the walls of the container or at the bottom.

Then the mixture is taken to the application container and it is continuously applied on the floor using a brush or roller. Do not keep the material in its container after mixing. This significantly shortens the pot life.

If required, an anti-slip coating can be produced by spreading medium or coarse size dry aggregate on the primer when it is still wet. It can be used in repairing wide cracks in the application area by mixing with quartz sand. Mixed material must be used within the pot life and thickened materials must not be thinned and used.

StenAst® 2EP MB is applied by brush and roller in one or two layers depending on the porosity and texture of the application surface. 400-600 microns applied at each layer. At that thickness, approximately 0.45-0.65 kg/m² is consumed per layer.

If primer application will be carried out as two layers, the second layer must be applied when the first layer is not completely cured and still tacky. In case the second layer is applied too late, adhesion will be negatively affected.

Pot life for **StenAst® 2EP MB** is affected by surface temperature. It should be kept in mind that surface temperature may be higher than the ambient temperature in summer but lower in winter.

5. Cleaning

Equipment used can be cleaned at the end of the job with **StenSolver EP**.

6. Safety

Applicators and supervisors must read Material Safety Data Sheet (MSDS) carefully and observe the considerations written therein. The application must be carried out by skilled workers under supervision of

experts and the applicators must use all kinds of protective equipment required for the worksite and the task such as goggles, mask and gloves.

Emptied packages must be handled in compliance with relevant regulations and laws.

7. Storage

The material must be kept away from sunlight in dry indoor storage. Recommended storage temperature is 10-30°C. Stored in these conditions, the shelf life of unopened containers are 12 months.

8. Company Liability

The information contained in this document is based on site experience of and laboratory tests done by **Stenkim®** and meant to give general information. It is the purchaser's responsibility to ensure applicability of products to their use. All **Stenkim®** products are available in specified quality and conditions. The company accepts no liability whatsoever unless the transportation, storage, application conditions and customer use are overseen by **Stenkim®**.

Stenkim® reserves the right to update all information contained in this document without notice.

9. Technical Data

Property	Result
Base Polymer	Epoxy
Solid Content % (A+B)	100
Color	Yellowish transparent
Density	1.05 ± 0.05 g/cm ³
Application Thickness, at each layer	400-600 microns
Pot Life of the Mixture @ 23 °C	25 minutes
Tack Free Time @ 23 °C	3 hours
Minimum Curing Time for Top Layer @23 °C	2 hours
Maximum Curing Time for Top Layer @23 °C	24 hours
Cure Time for Light Traffic @23 °C	24 hours
Complete Cure Time @ 23 °C	2 days

Stenkim® reserves the right to make changes in the values in this table at any time.