

1. Product Profile

StenMix® SUPA 130 is a ready to use polycarboxylic ether (PC) based, high range, water reducing, superplasticising admixture for Portland cement concrete.

StenMix® SUPA 130 conforms to requirements of TS EN 934-2 Table 3 (High Range Water Reducer/Plasticizer Standard) and ASTM C 494 Type F (Standard Specification for Chemical Admixtures for Concrete - Water Reducing, High Range Admixtures).

StenMix® SUPA 130 is available in 200 kg drums and 1,100 kg IBCs.

2. Uses

StenMix® SUPA 130 is suitable for production of highly flowable concrete to improve surface finish and density. It is especially suitable for use with floor slabs, foundations, ceilings, walls, beams and columns with densely packed reinforcements. It can also be used with high early strength precast and prestressed concrete or when early removal of form work is required.

StenMix® SUPA 130 substantially improves workability when added to premixed concrete. It eliminates the risk of segregation during concrete transport and placement. It reduces the amount of vibration required. It does not retard curing reaction of the concrete, so the curing time is not increased. It decreases the permeability of the concrete by decreasing amount of water required by 15% - 30% when dosage limits are observed

3. Application

The recommended dosage for StenMix® SUPA 130 is 0.5% to 2% based on weight of the cement. It should be added with the mixing water. Most preferably StenMix® SUPA 130 is added to the gauging water at the plant, it should not be added to dry cement.

Exact dosage must be determined by laboratory trial considering required workability and strength of concrete.

High Range Water Reducer Super Plasticizer

Highlights

- Polycarboxylic ether based high range water reducing, superplasticising admixture
- Improves surface finish and density
- Slump retentive
- Can be used with high early strength precast and prestressed concrete
- Improves workability
- Eliminates the risk of segregation during concrete transport and placement
- Reduces the amount of vibration required
- Decreases the permeability of the concrete by decreasing amount of water required by 15% - 30% when dosage limits are observed

5. Safety

Applicators and supervisors must read Material Safety Data Sheet (MSDS) carefully and observe the considerations written therein. Emptied packages must be handled in compliance with relevant regulations and laws.

6. Storage

The material must be kept in dry indoor storage. Recommended storage temperature is 0-30°C. Stored in these conditions, the shelf life is 12 months.

7. Company Liability

The information contained in this document is based on site experience of and laboratory tests done by Stenkim® and meant to give general information. It is the purchaser's responsibility to ensure applicability of products to their use. All Stenkim® products are available

in specified quality and conditions. The company accepts no liability whatsoever unless the transportation, storage, application conditions and customer use are overseen by Stenkim®.

Stenkim® reserves the right to update all information contained in this document without notice.

8. Technical Data

Properties	Results
Appearance - Color	Liquid – Amber
Chemical Structure	Modified Polycarboxylic Ether
Density	1.11kg/l ± 0.02kg/l
pH	8.30 ± 1.00
Solid content (by weight)	25% ± 1%
Chloride content	Less than 0.1%
Freezing Point	- 5 °C
Viscosity (@20°C)	60 cP ± 20 cP

Stenkim® reserves the right to make changes in the values in this table at any time.